

POSTALLOY® 2832-SPL (850-O/G)



Postle Industries • Cleveland, OH USA • Telephone: 216-265-9000 • Fax: 216-265-9030

Description

A premium chromium carbide alloy that has a high volume fraction of carbides dispersed in a hard matrix. For applications involving high abrasion and mild or moderate impact. Deposit polish in service and are heat resistant to 530°C. Use on carbon and low alloy steels.

Specifications

Product Type: Metal-cored, open-arc or gas-shielded
Deposits are slag-free

Weld Deposit Properties

Average Hardness: 58 - 62 HRc per ASTM E.18.0 & Mil 2540.0
Deposit Thickness: 1 to 2 layers
Deposits cannot be flame cut
Deposits will check-crack to relieve stresses

Applications

Scraper blades	Bucket teeth bucket sides and bottoms
Auger flights	Mixer blades
Road ripper teeth	Tillage tools
Screw conveyors	Fan blades

POSTALLOY® 2832-SPL Welding Parameters

Current: DC Straight or Reverse Polarity

Diameter	Amps	Volts
1.2mm	140-200	18-24
1.6mm	170-300	22-28

When welding out of position, use 1.2mm with reverse polarity and lower range of amperages and voltages. Weld vertical down with 16-20mm wide weave beads. A gas cover will be helpful, especially when using a constant current power source and voltage sensing feeder.

Packaging Options

Diameter	Standard Packaging
1.2mm	11.4kg spool
1.6mm	11.4kg spool